

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 02-179880

(43)Date of publication of application : 12.07.1990

(51)Int.Cl.

G23C 18/00

(21)Application number : 63-335057

(71)Applicant : TOYO SANSO KK

(22)Date of filing : 29.12.1988

(72)Inventor : KOKETSU AKINORI
KAMIOKA YASU HARU
SEKI HISASHI


(54) PRODUCTION OF THIN OXIDE CERAMIC SUPERCONDUCTING FILM

(57)Abstract:

PURPOSE: To form a thin oxide ceramic superconducting film by a simple process by spraying an aq. soln. of salts contg. metals as starting materials, feeding the resulting mist into oxygen plasma and depositing formed oxide ceramic on a substrate.

CONSTITUTION: An aq. soln. 1 of salts contg. metals as starting materials is introduced into a sprayer 2 and sprayed by ultrasonic spraying or other method to form mist of about 0.3-2.0 μ m particle size. This mist is introduced into the upper part of a reaction tube 4 with a first carrier gas 3 and a second carrier gas 5 is also introduced into the upper part. At this time, gaseous oxygen for generating oxygen plasma is incorporated into one or both of the carrier gases 3, 6 and the tube 4

is evacuated by a vacuum pump 11. Microwaves from a microwave oscillator 6 are guided with a waveguide 7, passed through the tube 4 and returned to the tube 4 by a plunger 8 to generate oxygen plasma 9. A thin oxide ceramic film having superior superconducting characteristics is formed on a substrate 10 set under the oxygen plasma generating region with high productivity.



PAT-NO: JP402179880A
DOCUMENT-IDENTIFIER: JP 02179880 A
TITLE: PRODUCTION OF THIN OXIDE CERAMIC
SUPERCONDUCTING FILM
PUBN-DATE: July 12, 1990

INVENTOR-INFORMATION:
NAME
KOKETSU, AKINORI
KAMIOKA, YASUHARU
SEKI, HISASHI

ASSIGNEE-INFORMATION:
NAME COUNTRY
TOYO SANZO KK N/A

APPL-NO: JP63335057
APPL-DATE: December 29, 1988
INT-CL (IPC): C23C018/00
US-CL-CURRENT: 505/809

ABSTRACT:

PURPOSE: To form a thin oxide ceramic superconducting film by a simple process by spraying an aq. soln. of salts contg. metals as starting materials, feeding the resulting mist into oxygen plasma and depositing formed oxide ceramic on a substrate.

CONSTITUTION: An aq. soln. 1 of salts contg. metals as starting materials is introduced into a sprayer 2 and sprayed by ultrasonic spraying or other method to form mist of about 0.3-2.0 μ m particle size. This mist is introduced into the upper part of a reaction tube 4 with a first carrier gas 3

and a second carrier gas 5 is also introduced into the upper part. At this time, gaseous oxygen for generating oxygen plasma is incorporated into one or both of the carrier gases 3, 6 and the tube 4 is evacuated by a vacuum pump 11. Microwaves from a microwave oscillator 6 are guided with a waveguide 7, passed through the tube 4 and returned to the tube 4 by a plunger 8 to generate oxygen plasma 9. A thin oxide ceramic film having superior superconducting characteristics is formed on a substrate 10 set under the oxygen plasma generating region with high productivity.

COPYRIGHT: (C)1990,JPO&Japio